



Manufacturer:
ÅngströmBond®

Product Name:
ÅngströmBond® AB9590 Thermally Conductive Black Epoxy,
Room Temperature Cure (2.5g)

Manufacturer Part Number:
AB9590-2.5G

▶ [Click here for more details on the ÅngströmBond® AB9590 Thermally Conductive Black Epoxy, Room Temperature Cure \(2.5g\)](#)

ÅngströmBond®

Adhesives

The only adhesive line developed exclusively for fiber optics

ÅngströmBond® AB9590 Flexible potting/bonding compound

Description:

ÅngströmBond® AB9590 is a two component, thermally conductive, high performance epoxy adhesive and potting compound. This room temperature curing adhesive is designed for use in applications that require a flexible material for sensitive or fragile components or fine electrical wires. AB9590 has a low mixed viscosity for ease of potting or brushing.

Typical Physical Properties:

Color Mixed:	Black
Specific Gravity Mixed:	1.28
Viscosity, cps:	30,000
Hardness, Shore A:	<80
Operating Temp, °C	-20 to 100
Thermal conductivity, @85°C W/m ² K	0.946

Handling Characteristics:

Working time @ 25°C (77F) - 45 minutes

Mix Ratio -

	RESIN	HARDENER
Color	Black	Lt. Yellow
Mix Ratio (by Volume)	3.67	1.00
Mix Ratio (by Weight)	100	15
Specific Gravity	1.56	1.01

Cure Schedule -

80% strength – 16 hours @ 25°C
100% full strength – 112 hours @ 25°C

Filler may settle during shipping and storage. Thorough mixing of bulk containers is recommended before use.

ÅngströmBond® is a registered trademark of Fiber Optic Center, Inc., New Bedford MA, USA

Fiber Optic Center™, Inc. MAKES NO EXPRESS OR IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS OR OTHERWISE, with respect to its products. In addition, while the information herein is believed to be reliable, no warranty is expressed or implied regarding the accuracy of the data or the results to be obtained from the use thereof. All recommendations or suggestion for use are made without guarantee -- inasmuch as conditions of use are beyond our control. The properties given are typical values, and are not intended for use in preparing specifications. Users should make their own test to determine the suitability of this product for their own purposes.

Contact the professionals at Fiber Optic Center for a quote or to get more details.

focenter.com • 508-992-6464 | (800) 473-4237 • sales@focenter.com

23 Centre Street • New Bedford, MA 02740 USA

Product specifications and data are subject to change without notice.